Product Data Sheet

TapTec™ HCRSS Na Ion Exchange Resin

Drinking Water-grade, Gel, Strong Acid Cation Exchange Resin for Domestic Softening

Description

TapTec™ HCRSS Na Ion Exchange Resin is a high-capacity, gel, strong acid cation exchange resin with excellent kinetics and good physical, chemical, and thermal stability. TapTec™ HCRSS Na can be used for domestic softening applications.

Applications

- Domestic softening

Typical Properties

Physical Properties	
Copolymer	Styrene-divinylbenzene
Matrix	Gel
Type	Strong acid cation
Functional Group	Sulfonic acid
Physical Form	White to amber, translucent, spherical beads
Chemical Properties	
Ionic Form as Shipped	Na^+
Total Exchange Capacity	≥ 1.9 eq/L
Water Retention Capacity	48 – 52%
Acidity Range	7.0 – 10.5
Particle Size [§]	
300 – 1200 µm	≥ 90%
< 300 µm	≤ 1%
Purity	
Color Throw, as packaged	≤ 20 APHA units
Stability	
Whole Uncracked Beads	≥ 90%
Swelling	$Ca^{2+} \rightarrow Na^+$: 5%
Density	
Particle Density	1.3 g/mL
Shipping Weight	800 g/L

[§] For additional particle size information, please refer to the Particle Size Distribution Cross Reference Chart (Form No. 45-D00954-en).

Form No. 45-D00843-en, Rev. 1
January 2022

Suggested Operating Conditions

Maximum Operating Temperature	120°C (248°F)
pH Range	0 – 14
Bed Depth, min.	800 mm (2.6 ft)
Flowrates	
Service	5 – 50 BV*/h (0.63 – 6.3 gpm/ft^3)
Backwash	See Figure 1
Regeneration	1 – 10 m/h (0.4 – 4 gpm/ft^2)
Displacement Rinse	1 – 10 m/h (0.4 – 4 gpm/ft^2)
Fast Rinse	5 – 50 BV/h (0.63 – 6.3 gpm/ft^3)
Total Rinse Requirement	3 – 6 BV
Regenerant	NaCl
Concentration	8 – 12%

* 1 BV (Bed Volume) = 1 m^3 solution per m^3 resin or 7.5 gal per ft^3 resin


Hydraulic Characteristics

Estimated bed expansion of TapTec™ HCRSS Na Ion Exchange Resin as a function of backwash flowrate and ionic form at 25°C (77°F) is shown in Figure 1. The flowrate necessary to achieve a desired bed expansion for other water temperatures can be calculated with the provided equations.

Estimated pressure drop for TapTec™ HCRSS Na as a function of service flowrate at 20°C (68°F) is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean water and a well-classified bed. Estimated pressure drop at other water temperatures can be calculated with the provided equations.

Figure 1: Backwash Expansion

Temperature = 25°C (77°F)




For other temperatures use:

$F_T = F_{25°C} [1 + 0.008 (1.8T_{°C} - 45)]$, where F ≡ m/h

$F_T = F_{77°F} [1 + 0.008 (T_{°F} - 77)]$, where F ≡ gpm/ft^2

Figure 2: Pressure Drop

Temperature = 20°C (68°F)



For other temperatures use:

$P_T = P_{20°C} / (0.026T_{°C} + 0.48)$, where P ≡ bar/m

$P_T = P_{68°F} / (0.014T_{°F} + 0.05)$, where P ≡ psi/ft

Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Form No. 45-D00843-en, Rev. 1
January 2022

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Regulatory Note

This product may be subject to drinking water application restrictions in some countries; please check the application status before use and sale.

Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2022 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

Form No. 45-D00843-en, Rev. 1
January 2022